

Corrispondenza tra le designazioni Rame

Italy	International Standard Organisation	Germany		United Kingdom	France	Switzerland	Spain		Sweden	Japan
UNI	ISO	DIN Kurzzeichen	Nummer	BS	NF	SN/VSM	UNE	Simbol	SIS	JIS
Cu-OF	Cu-OF	OF-Cu	2.0040	C110	Cu-c2	Cu-OFE	C-1120	Cu-OF	5011	C 1011
Cu-OF	Cu-OF	OF-Cu	2.0040	C111	Cu-c2	Cu-OFE	C-1120	Cu-OF	5011	C 1011
-	-	SE-Cu	2.0070	-	-	Cu-OFE	-	-	-	-
-	-	SE-Cu	2.0070	-	-	Cu-OFE	-	-	-	-
Cu-DLP	Cu-DLP	SW-Cu	2.0076	-	Cu-b2	Cu-DLP	C-1131	Cu-DLP	-	C 1201
Cu-DHP	Cu-DHP	SF-Cu	2.0090	C106	Cu-b1	Cu-DHP	C-1130	Cu-DHP	5015	C 1220
Cu-DHP	Cu-DHP	SF-Cu	2.0090	C106	Cu-b1	Cu-DHP	C-1130	Cu-DHP	5015	C 1220
Cu-DHP	Cu-DHP	SF-Cu	2.0090	C106	Cu-b1	Cu-DHP	C-1130	Cu-DHP	5015	C 1220
Cu-ETP	Cu-ETP	E-Cu57	2.0060	C101	Cu-a1	Cu-ETP	C-1110	Cu-ETP	5010	C 1100
Cu-ETP	Cu-ETP	E-Cu58	2.0065	C101	Cu-a1	Cu-ETP	C-1110	Cu-ETP	5010	C 1100
-	-	CuZn0,5	2.0205	-	-	-	-	-	-	-
CuNi2Si	CuNi2Si	CuNi2Si	2.0855	-	-	-	C-9435	CuNi2Si	-	-
-	-	-	-	-	-	-	-	-	-	-
CuCrZr	CuCrZr	CuCrZr	2-1293	CC10	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-
-	-	CuFe2p	2.1310	-	-	-	-	-	-	-